

precipitation hardening SAE HEV7 steel chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, We can produce round bars, forged rings, forged cakes, flat bars, tubes, sheets, plates, steel wires, steel strips, steel coils, etc. The size can be customized, the maximum order quantity is 100Kg. It also contains the use of **SAE HEV7**, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Materials Special Alloy precipitation hardening SAE HEV7

SAE HEV7 Standard Number									
ITEM	Stan	dard Num	ber	Descriptions					
SAE HEVZ Chemical composition(mass fraction)(wt.%)									
Chemical			Min.(%)			Max.(%)			
С	Si	Mn	Р	S	Cr	Ni	Мо	V	Та
0.08	0.70	1.50			14.75	26.0	1.25		
W	Ν	Cu	Со	Pb	В	Nb	AI	Ti	Other

SAE HEV7 Physical Properties					
Tensile strength	115-234	σb/MPa			
Yield Strength	23	σ 0.2 ≥/MPa			
Elongation	65	δ5≥ (%)			
Ψ	-	ψ≥ (%)			
Akv	-	Akv≥/J			
HBS	123-321				
HRC	30	-			

SAE HEV7 Mechanical Properties					
Tensile strength	231-231	σb/MPa			

+86-1388-0247-006 Email: sales@ccttc.com https://ccttc.com/ Page 1 / 3



CCTTC - SAE HEV7 Datasheet, Chemical Composition

precipitation hardening SAE HEV7 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, SAE HEV7 Supplier

Yield Strength	154	σ 0.2 ≥/MPa	
Elongation	56	δ5≥(%)	
Ψ	-	ψ≥(%)	
Akv	-	Akv≥/J	
HBS	235-268		
HRC	30		

SAE HEV7 Heat Treatment Regime					
Annealing	Quenching	Tempering	Normalizing	Q & T	
\checkmark	\checkmark	\checkmark	\checkmark	\checkmark	

SAE HEV7 Range of products					
Product type	Products	Dimension	Processes	Deliver Status	
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting	
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,	
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting	
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED	

We can produce Special Alloy the specifications follows:

Note:

- (1) listed in the table apex diameter (d), to steel thickness (a) multiples said.
- (2) in the ASTM A6 standard specified scope can meet any additional conditions.
- (3) from the standard for 50 mm (2 in).



CCTTC - SAE HEV7 Datasheet, Chemical Composition

precipitation hardening SAE HEV7 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, SAE HEV7 Supplier

Mechanical properties Mechanische Eigenschaften Caracteristiques mecaniques ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale Rm Tensile strength / Zugfestigkeit / Resistance a la traction A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal | Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc Round bar: Diameter : 1mm-2000mm Square bar: Size: 50mm * 50mm-600mm *600mm Plate steel/flat bar: Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm Tube/pipe: Size: OD: 6-219mm WT: 1-35 mm. Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm Length: We can supply any length based on the customer's requirement. Forging/hot rolling/ extrusion of steel. Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode. Ultrasonic inspection: 100% ultrasonic inspection for any inperfections or based on the customer's requirement. UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402 Excellent service for all kinds of industries, with advantages of technologies, equipment and price. We serve you with our honesty, integrity, and professionality.