

#### CCTTC - ISO X2CrNi12 Datasheet, Chemical Composition

ISO standard thermal deformation of stainless steel ISO X2CrNi12 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, ISO X2CrNi12 Supplier

ISO standard thermal deformation of stainless steel ISO X2CrNi12 steel chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, We can produce round bars, forged rings, forged cakes, flat bars, tubes, sheets, plates, steel wires, steel strips, steel coils, etc. The size can be customized, the maximum order quantity is 100Kg. It also contains the use of **ISO X2CrNi12**, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Materials Special Alloy ISO standard thermal deformation of stainless steel <a href="ISO">ISO</a> X2CrNi12

| <u>ISO X2CrNi12</u> Standard Number |                 |              |  |  |  |
|-------------------------------------|-----------------|--------------|--|--|--|
| ITEM                                | Standard Number | Descriptions |  |  |  |

| ISO X2CrNi12 Chemical composition(mass fraction)(wt.%) |              |          |              |              |               |          |         |    |       |
|--|--------------|----------|--------------|--------------|---------------|----------|---------|----|-------|
| Chemical   |              |          |              | Min.(%)      |               |          | Max.(%) |    |       |
| С  | Si           | Mn       | Р            | S            | Cr            | Ni       | Мо      | V  | Ta    |
| Max<br>0.030   | Max 1.00     | Max 1.50 | Max<br>0.040 | Max<br>0.015 | 10.5-12.<br>5 | 0.30-1.1 |         |    |       |
| W  | N            | Cu       | Со           | Pb           | В             | Nb       | Al      | Ti | Other |
|  | Max<br>0.030 |          |              |              |               |          |         |    |       |

| ISO X2CrNi12 Physical Properties |         |             |  |  |  |  |
|----------------------------------|---------|-------------|--|--|--|--|
| Tensile strength                 | 115-234 | σb/MPa      |  |  |  |  |
| Yield Strength                   | 23      | σ 0.2 ≥/MPa |  |  |  |  |
| Elongation                       | 65      | δ5≥ (%)     |  |  |  |  |
| Ψ                                | -       | ψ≥ (%)      |  |  |  |  |
| Akv                              | -       | Akv≥/J      |  |  |  |  |
| HBS                              | 123-321 | -           |  |  |  |  |
| HRC                              | 30      | -           |  |  |  |  |



### **CCTTC - ISO X2CrNi12 Datasheet, Chemical Composition**

ISO standard thermal deformation of stainless steel ISO X2CrNi12 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, ISO X2CrNi12 Supplier

| ISO X2CrNi12 Mechanical Properties |         |             |  |  |  |  |
|------------------------------------|---------|-------------|--|--|--|--|
| Tensile strength                   | 231-231 | σb/MPa      |  |  |  |  |
| Yield Strength                     | 154     | σ 0.2 ≥/MPa |  |  |  |  |
| Elongation                         | 56      | δ5≥(%)      |  |  |  |  |
| Ψ                                  | -       | ψ≥(%)       |  |  |  |  |
| Akv                                | -       | Akv≥/J      |  |  |  |  |
| HBS                                | 235-268 | -           |  |  |  |  |
| HRC                                | 30      | -           |  |  |  |  |

| ISO X2CrNi12 Heat Treatment Regime |              |              |              |           |  |  |
|------------------------------------|--------------|--------------|--------------|-----------|--|--|
| Annealing                          | Quenching    | Tempering    | Normalizing  | Q & T     |  |  |
| $\checkmark$                       | $\checkmark$ | $\checkmark$ | $\checkmark$ | $\sqrt{}$ |  |  |

| ISO X2CrNi12 Range of products |  |                               |   |  |  |  |
|--------------------------------|--|-------------------------------|---|--|--|--|
| Product type                   | Products                                       | Dimension                     | Processes   | Deliver Status   |  |  |
| Plates / Sheets                | Plates / Sheets                                | 0.08-200mm(T)*W*L             | Forging, hot rolling and cold rolling             | Annealed, Solution<br>and Aging, Q+T,<br>ACID-WASHED, Shot<br>Blasting |  |  |
| Steel Bar                      | Round Bar, Flat Bar,<br>Square Bar             | Φ8-1200mm*L                   | Forging, hot rolling<br>and cold rolling,<br>Cast | Black, Rough<br>Turning, Shot<br>Blasting,                             |  |  |
| Coil / Strip                   | Steel Coil /Steel<br>Strip                     | 0.03-16.0x1200mm              | Cold-Rolled & Hot-<br>Rolled                      | Annealed, Solution<br>and Aging, Q+T,<br>ACID-WASHED, Shot<br>Blasting |  |  |
| Pipes / Tubes                  | Seamless<br>Pipes/Tubes, Welded<br>Pipes/Tubes | OD:6-219mm x<br>WT:0.5-20.0mm | Hot extrusion, Cold<br>Drawn, Welded              | Annealed, Solution<br>and Aging, Q+T,<br>ACID-WASHED                   |  |  |

# We can produce Special Alloy the specifications



### CCTTC - ISO X2CrNi12 Datasheet, Chemical Composition

ISO standard thermal deformation of stainless steel ISO X2CrNi12 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, ISO X2CrNi12 Supplier

## follows:

Note:

(1) listed in the table apex diameter (d), to steel thickness (a) multiples said.

(2) in the ASTM A6 standard specified scope can meet any additional conditions.

(3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften

Caracteristiques mecaniques

ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale

Rm Tensile strength / Zugfestigkeit / Resistance a la traction

A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal

J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar:

Diameter: 1mm-2000mm

Square bar:

Size: 50mm \* 50mm-600mm \*600mm

Plate steel/flat bar:

Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm

Tube/pipe:

Size: OD: 6-219mm WT: 1-35 mm.

Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm

Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm

Length: We can supply any length based on the customer's requirement.

Forging/hot rolling/ extrusion of steel.

Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes

Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching +

tempering/any conditions based on the customer's requirement

Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on

the customer's requirement

Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable

electrode.

Ultrasonic inspection: 100% ultrasonic inspection for any inperfections or based on the customer's requirement.

UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402

Excellent service for all kinds of industries, with advantages of technologies, equipment and price.

We serve you with our honesty, integrity, and professionality.