

Spain structural alloy steel GP280GH steel chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, We can produce round bars, forged rings, forged cakes, flat bars, tubes, sheets, plates, steel wires, steel strips, steel coils, etc. The size can be customized, the maximum order quantity is 100Kg. It also contains the use of **GP280GH**, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Materials Special Alloy Spain structural alloy steel GP280GH

| GP280GH Standard Number                           |      |               |       |              |    |    |         |    |       |
|---|------|---------------|-------|--------------|----|----|---------|----|-------|
| ITEM  | Stan | dard Num      | nber  | Descriptions |    |    |         |    |       |
|   |      |               |       |              |    |    |         |    |       |
| GP280GH Chemical composition(mass fraction)(wt.%) |      |               |       |              |    |    |         |    |       |
| Chemical  |      |               |       | Min.(%)      |    |    | Max.(%) |    |       |
| С   | Si   | Mn            | Р     | S            | Cr | Ni | Мо      | V  | Та    |
| 0.18-0.2<br>5                                     | 0.6  | 0.80-1.2<br>0 | 0.035 | 0.02         |    |    |         |    |       |
| W   | Ν    | Cu            | Со    | Pb           | В  | Nb | AI      | Ti | Other |
|   |      |               |       |              |    |    |         |    |       |

| GP280GH Physical Properties |         |             |  |  |  |  |
|-----------------------------|---------|-------------|--|--|--|--|
| Tensile strength            | 115-234 | σb/MPa      |  |  |  |  |
| Yield Strength              | 23      | σ 0.2 ≥/MPa |  |  |  |  |
| Elongation                  | 65      | δ5≥ (%)     |  |  |  |  |
| Ψ                           | -       | ψ≥ (%)      |  |  |  |  |
| Akv                         | -       | Akv≥/J      |  |  |  |  |
| HBS                         | 123-321 | -           |  |  |  |  |
| HRC                         | 30      |             |  |  |  |  |

**GP280GH Mechanical Properties** 



## **CCTTC - GP280GH Datasheet, Chemical Composition**

Spain structural alloy steel GP280GH Mechanical properties, Physical properties, Mechanical properties, Heat treatment, GP280GH Supplier

| Tensile strength | 231-231 | σb/MPa      |  |
|------------------|---------|-------------|--|
| Yield Strength   | 154     | σ 0.2 ≥/MPa |  |
| Elongation       | 56      | δ5≥(%)      |  |
| Ψ                | -       | ψ≥(%)       |  |
| Akv              | -       | Akv≥/J      |  |
| HBS              | 235-268 |             |  |
| HRC              | 30      |             |  |

| GP280GH Heat Treatment Regime |              |              |              |              |  |  |
|-------------------------------|--------------|--------------|--------------|--------------|--|--|
| Annealing                     | Quenching    | Tempering    | Normalizing  | Q & T        |  |  |
| $\checkmark$                  | $\checkmark$ | $\checkmark$ | $\checkmark$ | $\checkmark$ |  |  |

| GP280GH Range of products |  |                               |   |  |  |
|---------------------------|--|-------------------------------|---|--|--|
| Product type              | Products                                       | ucts Dimension I              |   | Deliver Status   |  |
| Plates / Sheets           | Plates / Sheets                                | 0.08-200mm(T)*W*L             | Forging, hot rolling<br>and cold rolling          | Annealed, Solution<br>and Aging, Q+T,<br>ACID-WASHED, Shot<br>Blasting |  |
| Steel Bar                 | Round Bar, Flat Bar,<br>Square Bar             | Φ8-1200mm*L                   | Forging, hot rolling<br>and cold rolling,<br>Cast | Black, Rough<br>Turning, Shot<br>Blasting,                             |  |
| Coil / Strip              | Steel Coil /Steel<br>Strip                     | 0.03-16.0x1200mm              | Cold-Rolled & Hot-<br>Rolled                      | Annealed, Solution<br>and Aging, Q+T,<br>ACID-WASHED, Shot<br>Blasting |  |
| Pipes / Tubes             | Seamless<br>Pipes/Tubes, Welded<br>Pipes/Tubes | OD:6-219mm x<br>WT:0.5-20.0mm | Hot extrusion, Cold<br>Drawn, Welded              | Annealed, Solution<br>and Aging, Q+T,<br>ACID-WASHED                   |  |

## We can produce Special Alloy the specifications follows:

Note:

(1) listed in the table apex diameter (d), to steel thickness (a) multiples said.



## CCTTC - GP280GH Datasheet, Chemical Composition

Spain structural alloy steel GP280GH Mechanical properties, Physical properties, Mechanical properties, Heat treatment, GP280GH Supplier

(2) in the ASTM A6 standard specified scope can meet any additional conditions. (3) from the standard for 50 mm (2 in). Mechanical properties Mechanische Eigenschaften Caracteristiques mecaniques ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale Rm Tensile strength / Zugfestigkeit / Resistance a la traction A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc Round bar: Diameter: 1mm-2000mm Square bar: Size: 50mm \* 50mm-600mm \*600mm Plate steel/flat bar: Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm Tube/pipe: Size: OD: 6-219mm WT: 1-35 mm. Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm Length: We can supply any length based on the customer's requirement. Forging/hot rolling/ extrusion of steel. Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode. Ultrasonic inspection: 100% ultrasonic inspection for any inperfections or based on the customer's requirement. UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402 Excellent service for all kinds of industries, with advantages of technologies, equipment and price. We serve you with our honesty, integrity, and professionality.