

**CCTTC - A 693 S17700 Datasheet, Chemical Composition** Precipitation-Hardening Stainless and Heat-Resisting Steel Plate, Sheet, and Strip A 693 S17700 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, A 693 S17700 Supplier

Precipitation-Hardening Stainless and Heat-Resisting Steel Plate, Sheet, and Strip A 693 S17700 steel chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, We can produce round bars, forged rings, forged cakes, flat bars, tubes, sheets, plates, steel wires, steel strips, steel coils, etc. The size can be customized, the maximum order quantity is 100Kg. It also contains the use of **A 693 S17700**, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Materials Stainless Steels & Special Steels Precipitation-Hardening Stainless and Heat-Resisting Steel Plate, Sheet, and Strip <u>A 693 S17700</u>

| A 693 S17700 Standard Number |                 |   |  |  |
|------------------------------|-----------------|---|--|--|
| ITEM                         | Standard Number | Descriptions  |  |  |
| 1                            | A 693 (2006)    | Precipitation-Hardening Stainless and Heat-Resisting Steel Plate,<br>Sheet, and Strip |  |  |

| A 693 517700 Chemical composition(mass fraction)(wt.%) |    |    |    |         |    |    |         |    |       |
|--|----|----|----|---------|----|----|---------|----|-------|
| Chemical   |    |    |    | Min.(%) |    |    | Max.(%) |    |       |
|  | С  |    |    |         |    |    | 0.09    |    |       |
|  | Mn |    |    |         |    |    | 1.00    |    |       |
|  | Si |    |    |         |    |    | 1.00    |    |       |
|  | Р  |    |    |         |    |    | 0.04    |    |       |
|  | S  |    |    |         |    |    | 0.04    |    |       |
| Cr   |    |    |    | 16.00   |    |    | 18.00   |    |       |
|  | Ni |    |    | 6.50    |    |    | 7.75    |    |       |
|  | Мо |    |    |         |    |    |         |    |       |
|  | Al |    |    | 0.75    |    |    | 1.50    |    |       |
| С  | Si | Mn | Р  | S       | Cr | Ni | Мо      | V  | Та    |
|  |    |    |    |         |    |    |         |    |       |
| W  | N  | Cu | Со | Pb      | В  | Nb | AI      | Ti | Other |



## **CCTTC - A 693 S17700 Datasheet, Chemical Composition**

Precipitation-Hardening Stainless and Heat-Resisting Steel Plate, Sheet, and Strip A 693 S17700 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, A 693 S17700 Supplier

| A 693 S17700 Physical Properties |         |             |  |  |  |
|----------------------------------|---------|-------------|--|--|--|
| Tensile strength                 | 115-234 | σb/MPa      |  |  |  |
| Yield Strength                   | 23      | σ 0.2 ≥/MPa |  |  |  |
| Elongation                       | 65      | δ5≥ (%)     |  |  |  |
| Ψ                                | -       | ψ≥ (%)      |  |  |  |
| Akv                              |         | Akv≥/J      |  |  |  |
| HBS                              | 123-321 |             |  |  |  |
| HRC                              | 30      | -           |  |  |  |

| A 693 S17700 Mechanical Properties |         |             |  |  |  |
|------------------------------------|---------|-------------|--|--|--|
| Tensile strength                   | 231-231 | σb/MPa      |  |  |  |
| Yield Strength                     | 154     | σ 0.2 ≥/MPa |  |  |  |
| Elongation                         | 56      | δ5≥(%)      |  |  |  |
| Ψ                                  | -       | ψ≥(%)       |  |  |  |
| Akv                                | -       | Akv≥/J      |  |  |  |
| HBS                                | 235-268 | -           |  |  |  |
| HRC                                | 30      |             |  |  |  |

| A 693 S17700 Heat Treatment Regime              |              |              |              |              |  |
|---|--------------|--------------|--------------|--------------|--|
| Annealing Quenching Tempering Normalizing Q & T |              |              |              |              |  |
| $\checkmark$                                    | $\checkmark$ | $\checkmark$ | $\checkmark$ | $\checkmark$ |  |

| A 693 S17700 Range of products |                 |                   |  |  |  |
|--------------------------------|-----------------|-------------------|--|--|--|
| Product type                   | Products        | Dimension         | Processes                                | Deliver Status   |  |
| Plates / Sheets                | Plates / Sheets | 0.08-200mm(T)*W*L | Forging, hot rolling<br>and cold rolling | Annealed, Solution<br>and Aging, Q+T,<br>ACID-WASHED, Shot<br>Blasting |  |



## CCTTC - A 693 S17700 Datasheet, Chemical Composition

Precipitation-Hardening Stainless and Heat-Resisting Steel Plate, Sheet, and Strip A 693 S17700 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, A 693 S17700 Supplier

| Steel Bar     | Round Bar, Flat Bar,<br>Square Bar             | Φ8-1200mm*L                   | Forging, hot rolling<br>and cold rolling,<br>Cast | Black, Rough<br>Turning, Shot<br>Blasting,                             |
|---------------|--|-------------------------------|---|--|
| Coil / Strip  | Steel Coil /Steel<br>Strip                     | 0.03-16.0x1200mm              | Cold-Rolled & Hot-<br>Rolled                      | Annealed, Solution<br>and Aging, Q+T,<br>ACID-WASHED, Shot<br>Blasting |
| Pipes / Tubes | Seamless<br>Pipes/Tubes, Welded<br>Pipes/Tubes | OD:6-219mm x<br>WT:0.5-20.0mm | Hot extrusion, Cold<br>Drawn, Welded              | Annealed, Solution<br>and Aging, Q+T,<br>ACID-WASHED                   |

## We can produce Stainless Steels & Special Steels the specifications follows:

Note:

(1) listed in the table apex diameter (d), to steel thickness (a) multiples said.

- (2) in the ASTM A6 standard specified scope can meet any additional conditions.
- (3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften

Caracteristiques mecaniques

ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale Rm Tensile strength / Zugfestigkeit / Resistance a la traction

A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal

J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar: Diameter : 1mm-2000mm Square bar: Size: 50mm \* 50mm-600mm \*600mm Plate steel/flat bar: Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm Tube/pipe: Size: OD: 6-219mm WT: 1-35 mm. Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm Length: We can supply any length based on the customer's requirement. Forging/hot rolling/ extrusion of steel. Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on



## CCTTC - A 693 S17700 Datasheet, Chemical Composition

Precipitation-Hardening Stainless and Heat-Resisting Steel Plate, Sheet, and Strip A 693 S17700 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, A 693 S17700 Supplier

the customer's requirement

Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode.

Ultrasonic inspection: 100% ultrasonic inspection for any inperfections or based on the customer's requirement.

UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402

Excellent service for all kinds of industries, with advantages of technologies, equipment and price. We serve you with our honesty, integrity, and professionality.