



CCTTC - B 883 MIM-2200 Datasheet, Chemical Composition

Standard Specification for Metal Injection Molding (MIM) Ferrous Materials B 883 MIM-2200 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, B 883 MIM-2200 Supplier

Standard Specification for Metal Injection Molding (MIM) Ferrous Materials [B 883 MIM-2200](#) steel chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, We can produce round bars, forged rings, forged cakes, flat bars, tubes, sheets, plates, steel wires, steel strips, steel coils, etc. The size can be customized, the maximum order quantity is 100Kg. It also contains the use of **B 883 MIM-2200**, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Materials Stainless Steels & Special Steels Standard Specification for Metal Injection Molding (MIM) Ferrous Materials [B 883 MIM-2200](#)

[B 883 MIM-2200](#) Standard Number

ITEM	Standard Number	Descriptions
1	B 883 (2010)	Standard Specification for Metal Injection Molding (MIM) Ferrous Materials

[B 883 MIM-2200](#) Chemical composition(mass fraction)(wt.%)

Chemical	Min.(%)	Max.(%)
C		0.13
Si		
Mn		
Ni		
Cr		5.70
Al		6.30
Cu		
Ti		
Fe		
Mo		2.00
Co		
Ta		3.00
Zr		0.60



CCTTC - B 883 MIM-2200 Datasheet, Chemical Composition

Standard Specification for Metal Injection Molding (MIM) Ferrous Materials B 883 MIM-2200 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, B 883 MIM-2200 Supplier

W							11.00		
C	Si	Mn	P	S	Cr	Ni	Mo	V	Ta
W	N	Cu	Co	Pb	B	Nb	Al	Ti	Other

B 883 MIM-2200 Physical Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	$Akv \geq$ /J
HBS	123-321	-
HRC	30	-

B 883 MIM-2200 Mechanical Properties

Tensile strength	231-231	σ_b /MPa
Yield Strength	154	$\sigma_{0.2} \geq$ /MPa
Elongation	56	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	$Akv \geq$ /J
HBS	235-268	-
HRC	30	-

B 883 MIM-2200 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√



CCTTC - B 883 MIM-2200 Datasheet, Chemical Composition

Standard Specification for Metal Injection Molding (MIM) Ferrous Materials B 883 MIM-2200 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, B 883 MIM-2200 Supplier

B 883 MIM-2200 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

We can produce Stainless Steels & Special Steels the specifications follows:

Note:

- (1) listed in the table apex diameter (d), to steel thickness (a) multiples said.
- (2) in the ASTM A6 standard specified scope can meet any additional conditions.
- (3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften

Caracteristiques mecaniques

ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'élasticite minimale

Rm Tensile strength / Zugfestigkeit / Resistance a la traction

A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal

J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar:

Diameter : 1mm-2000mm

Square bar:

Size: 50mm * 50mm-600mm *600mm

Plate steel/flat bar:

Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm

Tube/pipe:

Size: OD: 6-219mm WT: 1-35 mm.



CCTTC - B 883 MIM-2200 Datasheet, Chemical Composition

Standard Specification for Metal Injection Molding (MIM) Ferrous Materials B 883 MIM-2200 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, B 883 MIM-2200 Supplier

Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm

Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm

Length: We can supply any length based on the customer's requirement.

Forging/hot rolling/ extrusion of steel.

Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes

Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement

Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement

Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode.

Ultrasonic inspection: 100% ultrasonic inspection for any imperfections or based on the customer's requirement.

UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402

Excellent service for all kinds of industries, with advantages of technologies, equipment and price.

We serve you with our honesty, integrity, and professionalism.