

Alloyed Si steel 70Si7 steel chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, We can produce round bars, forged rings, forged cakes, flat bars, tubes, sheets, plates, steel wires, steel strips, steel coils, etc. The size can be customized, the maximum order quantity is 100Kg. It also contains the use of **70Si7**, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

| 70Si7 Standard Number | | | | | | | | | |
|-----------------------|-----------------|------------|------------|--------------|--------------|--------------|---------|----|-------|
| ITEM | Standard Number | | | Descriptions | | | | | |
| | | | | | | | | | |
| | | <u>705</u> | i7 Chemica | al composit | ion(mass fra | action)(wt.9 | %) | | |
| Chemical | | | | Min.(%) | | | Max.(%) | | |
| С | | | | 0.65 | | | 0.75 | | |
| Si | | | | 1.50 | | | 1.80 | | |
| Mn | | | | 0.60 | | | 0.80 | | |
| Р | | | | | | | 0.030 | | |
| S | | | | 0.030 | | | | | |
| Cr | | | | | | | | | |
| Мо | | | | | | | | | |
| | V | | | | | | | | |
| С | Si | Mn | Р | S | Cr | Ni | Мо | V | Та |
| | | | | | | | | | |
| W | Ν | Cu | Со | Pb | В | Nb | Al | Ti | Other |
| | | | | | | | | | |

Data Table for Materials Tool Steels & Die Steels Alloyed Si steel 70Si7

| 70Si7 Physical Properties | | | | | | |
|---------------------------|---------|-------------|--|--|--|--|
| Tensile strength | 115-234 | σb/MPa | | | | |
| Yield Strength | 23 | σ 0.2 ≥/MPa | | | | |

+86-1388-0247-006 Email: sales@ccttc.com https://ccttc.com/ Page 1 / 4



CCTTC - 70Si7 Datasheet, Chemical Composition Alloyed Si steel 70Si7 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, 70Si7 Supplier

| Elongation | 65 | δ5≥ (%) |
|------------|---------|---------|
| Ψ | - | ψ≥ (%) |
| Akv | | Akv≥/J |
| HBS | 123-321 | - |
| HRC | 30 | - |

| 70Si7 Mechanical Properties | | | | | | |
|-----------------------------|---------|-------------|--|--|--|--|
| Tensile strength | 231-231 | σb/MPa | | | | |
| Yield Strength | 154 | σ 0.2 ≥/MPa | | | | |
| Elongation | 56 | δ5≥(%) | | | | |
| Ψ | - | ψ≥(%) | | | | |
| Akv | - | Akv≥/J | | | | |
| HBS | 235-268 | - | | | | |
| HRC | 30 | - | | | | |

| 70Si7 Heat Treatment Regime | | | | | |
|-----------------------------|--------------|--------------|--------------|--------------|--|
| Annealing Quenching | | Tempering | Normalizing | Q & T | |
| \checkmark | \checkmark | \checkmark | \checkmark | \checkmark | |

| 70Si7 Range of products | | | | | | |
|-------------------------|------------------------------------|-------------------|---|--|--|--|
| Product type | Products | Dimension | Processes | Deliver Status | | |
| Plates / Sheets | Plates / Sheets | 0.08-200mm(T)*W*L | Forging, hot rolling and cold rolling | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting | | |
| Steel Bar | Round Bar, Flat Bar, Square Bar | Φ8-1200mm*L | Forging, hot rolling and cold rolling, Cast | Black, Rough Turning, Shot Blasting, | | |
| Coil / Strip | Steel Coil /Steel Strip | 0.03-16.0x1200mm | Cold-Rolled & Hot- Rolled | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting | | |



CCTTC - 70Si7 Datasheet, Chemical Composition

Alloyed Si steel 70Si7 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, 70Si7 Supplier

Pipes / Tubes

Seamless Pipes/Tubes, Welded Pipes/Tubes OD:6-219mm x WT:0.5-20.0mm Hot extrusion, Cold Drawn, Welded Annealed, Solution and Aging, Q+T, ACID-WASHED

We can produce Tool Steels & Die Steels the specifications follows:

Note:

(1) listed in the table apex diameter (d), to steel thickness (a) multiples said.

(2) in the ASTM A6 standard specified scope can meet any additional conditions.

(3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften

Caracteristiques mecaniques

ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale Rm Tensile strength / Zugfestigkeit / Resistance a la traction

A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal

J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar: Diameter : 1mm-2000mm Square bar: Size: 50mm * 50mm-600mm *600mm Plate steel/flat bar: Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm Tube/pipe: Size: OD: 6-219mm WT: 1-35 mm. Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm Length: We can supply any length based on the customer's requirement. Forging/hot rolling/ extrusion of steel. Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/guenching + tempering/any conditions based on the customer's requirement Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode. Ultrasonic inspection: 100% ultrasonic inspection for any inperfections or based on the customer's requirement. UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402

+86-1388-0247-006 Email: sales@ccttc.com https://ccttc.com/ Page 3 / 4



CCTTC - 70Si7 Datasheet, Chemical Composition Alloyed Si steel 70Si7 Mechanical properties, Physical properties, Mechanical properties, Heat treatment, 70Si7 Supplier

Excellent service for all kinds of industries, with advantages of technologies, equipment and price. We serve you with our honesty, integrity, and professionality.